

Name of The Product : 9,7x9,7 Veinstone Series (30x40)  
Production Facility : Floor Tile Factory  
Product Group : Dry-pressed ceramic tiles / Group Blb/ GL  
Recommended Use : Interior & exterior floor  
General Properties : Mat  
Report Date : 21.07.2024

Test Title	Test Results	Requirements	Desicion
Length & Width (mm)	96,8 – 97,3 mm	96,5 – 97,5 mm	OK
Thickness (mm)	7,0 mm	6,7 – 7,3 mm	OK
Straightness of Sides (%)	± %0,2	± %0,5	OK
Rectangularity (%)	± %0,2	± %0,6	OK
Edge Curvature (%)	± %0,2	± %0,5	OK
Corner Curvature (%)	± %0,2	± %0,5	OK
Center Curvature (%)	± %0,2	± %0,5	OK
Small Colour Differences	First Quality	> %95 perfect	OK
Water Absorption	2,10 %	0,5 % < E ≤ 3,0 %	OK
Breaking Strength (N)	> 1100N	> 700 N	OK
Modulus of Rupture (N/mm <sup>2</sup> )	> 32 N/mm <sup>2</sup>	> 30 N/mm <sup>2</sup>	OK
Abrasion Resistance (PEI)	Bone:IV Midgrey:IV Vizon:III White:IV	As declared	OK
Coeff. Of Thermal Expansion	< 7,0 x 10 <sup>-6</sup>	As declared	OK
Thermal Shock Resistance	Resistant	Required	OK
Crazing Resistance	Resistant	Required	OK
Frost Resistance	Resistant	Required	OK
Coefficient of Friction (μ)	~62,0	As declared	OK
Moisture Expansion (mm/m)	< 0,3	As declared	OK
Impact Resistance	Resistant	As declared	OK
Staining Resistance	Class 5	Min. Class 3	OK
Resistance to low conc. of Acid & Alkalis	B	As declared	OK
Resistance to high conc. of Acid & Alkalis	B	As declared	OK
Household Chemicals	A	Min. B	OK
Release of Cadmium	< 0,07 mg/dm <sup>2</sup>	As declared	OK
Release of Lead	< 0,8 mg/dm <sup>2</sup>	As declared	OK
OVERALL RESULT	All test results are positive according to the norms of ISO 13006 and EN 14411 standards, Annex H.		

Prepared by  
Kağan Kurnaz  
Quality Assurance Staff

Approved by  
Ahmet Pehlivan  
Quality Assurance Manager