

Technical Datasheet - Atlantic 8

Direct Pressure Laminate, Level of use according to EN 13329: class **23/32 – AC4**



Heavy domestic use



General commercial use

DIMENSION

dimension	thickness (d)	$8 \pm 0,50 \text{ mm} \cdot d_{\text{max}} - d_{\text{min}} \leq 0,50 \text{ mm}$		
	length	$1288 \pm 0,50 \text{ mm}$		
	width (b)	$195 \pm 0,10 \text{ mm} \cdot b_{\text{max}} - b_{\text{min}} \leq 0,20 \text{ mm}$		
profile	long side	twin clic+	short side	1clic 2go pure+
groove	long side	v-groove	short side	v-groove

TOLERANCE

squareness	EN 13329	$\leq 0,20 \text{ mm}$
straightness	EN 13329	$\leq 0,30 \text{ mm}$
flatness crosswise	EN 13329	concave: $\leq 0,15\%$ · convex: $\leq 0,20\%$
flatness length	EN 13329	concave: $\leq 0,50\%$ · convex: $\leq 1,00\%$
gaps between elements	EN 13329	average: $\leq 0,15 \text{ mm}$ · max: $\leq 0,20 \text{ mm}$
height difference between elements	EN 13329	average: $\leq 0,10 \text{ mm}$ · max: $\leq 0,15 \text{ mm}$
misalignment		$\pm 2 \text{ mm}$

TEST

abrasion resistance		EN 13329	AC4 (≥ 4000 rpm)
impact resistance		EN 13329	small ball ≥ 35 mm · big ball ≥ 600 mm
stain resistance	group 1 & 2	EN 13329	grade 5
	group 3		≥ grade 4
castor chair test		EN 13329	no change in appearance or damage, as defined per EN 425
effect of a furniture leg		EN 13329	no damage shall be visible, when testet with foot type 0
static indentation		EN 13329	≤ 0,05 mm
light fastness		EN 13329	grey scale ≥ 4 at blue wool grade 6
dimensional variations after changes in relative humidity		EN 13329	lengthwise ≤ 0,9 mm · crosswise ≤ 0,9 mm
locking strength		EN 13329	length ≥ 1 kN/m · width ≥ 2 kN/m
surface soundness		EN 13329	≥ 1,25 N/mm²

ENVIRONMENT

emission of formaldehyde	EN 16516	class E1
--------------------------	----------	----------

PHYSICAL BEHAVIOR

fire behavior	EN 13501-1	Cfl s1
slide resistance	EN 13893	technical class DS
thermal resistance	EN 12667	$0,073 \text{ (m}^2\text{K)/W} \pm 15\%$
thermal conductivity	EN 12664	$0,110 \text{ W/(m}^*\text{K)} \pm 15\%$