

TECHNICAL FEATURES			
Collection: Cementum Surface: Natural		Brand: Marazzi	
Size (cm): 120x120 RT		Thickness (mm): 06	

Compliant with standard EN 14411:2016 annex G group Bla - UGL

Compliant with standard ISO 13006:2018 annex G group Bla - UGL

Technical Features	Testing Method	Meas. unit	Average Typical Values	Established limits				
DIMENSIONAL PROPERTIES AND SURFACE QUALITY								
Dimensions				Nominal Length of edge N (cm) 7≤N<15	Nominal Length of edge N (cm) N≥15			
Length and width (*)	ISO 10545-2	(mm) (%)	Complies with the standards	±2% (max 5mm)	±2% (max 5mm) ±2% (max 5mm)			
Length and width (**)								
Not Rectified			Complies with the standards	±0,9 mm	±0,6%	±2,0 mm		
Rectified				± 0,4 mm	±0,3 %	±1,0 mm		
Thickness			Complies with the standards	±0,5 mm	±5%	±0,5 mm		
Not Rectified				±0,5 mm	±5%	±0,5 mm		
Rectified								
Straightness of sides			Complies with the standards	±0,75 mm	±0,5 %	±1,5 mm		
Not Rectified				±0,4 mm	±0,3 %	±0,8 mm		
Rectified								
Rectangularity			Complies with the standards	±0,75 mm	±0,5%	±2,0 mm		
Not Rectified				±0,4 mm	±0,3%	±1,5 mm		
Rectified								
Surface Flatness c.c - e.c. - w.			Complies with the standards	±0,75 mm	±0,5%	±2,0 mm		
Not Rectified				±0,6 mm	±0,4%	±1,8 mm		
Rectified								
Surface Quality			Complies with the standards			≥95%		
PHYSICAL PROPERTIES								
Water absorption			ISO 10545-3	(%)	≤ 0,5	Eb ≤ 0,5 (Individual maximum value 0,6%)		
Modulus of rupture	ISO 10545-4	(N/mm2)	> 35	R ≥35 (Individual minimun value 32 N/mm2)				
Breaking Strength	ISO 10545-4	(N)	> 700	≥1300 (Thickness ≥7,5 mm) ≥700 (Thickness < 7,5 mm)				
Resistance to deep abrasion	ISO 10545-6	(mm3)	≤ 175	≤175				
Resistance to surface abrasion	Internal Method		Intended use - Class H					
Linear thermal expansion coefficient	ISO 10545-8	(x(10)-6/°C)	≤ 9	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)				
Thermal shock resistance	ISO 10545-9		Complies with the standards	Declared value (EN 14411:2016) **** Test Method available (ISO 13006:2018)				
Frost resistance	ISO 10545-12		Complies with the standards	Pass according to EN ISO 10545-1 (EN 14411:2016) Required (ISO 13006:2018)				
Reaction to fire	-	-	Floor/Wall Class A1 FL / A1	Class A1 or Class A1 FL				
Colour resistance to light exposure	DIN 51094		Complies with the standards	No sample must show noticeable colour modifications.				



TECHNICAL FEATURES	
Collection: Cementum Surface: Natural	Brand: Marazzi
Size (cm): 120x120 RT	Thickness (mm): 06

Technical Features	Testing Method	Meas. unit	Average Typical Values	Established limits
CHEMICAL PROPERTIES				
Resistance to chemicals for household use and swimming pool salts	ISO 10545-13		A	UB Minimum (EN 14411:2016) UB Minimum (ISO 13006:2018)
Resistance to low concentrations of acids and alkalis	ISO 10545-13		LA-LB	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)
Resistance to high concentrations of acids and alkalis	ISO 10545-13		HA-HB	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)
Stain resistance	ISO 10545-14		from Class 5 to Class 3	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)

ANTISLIPPERY PROPERTIES				
Slipperiness Resistance: Ramp Method	DIN 51130 DGUV Regel 108-003		R10	from R9 to R13
Slipperiness Resistance: Ramp Method	DIN 51097 DGUV Information 207-006		B(A+B)	from A to C
Slipperiness Resistance: B.C.R.	D.M. N.236 14/6/89		$\mu > 0,40$	$\mu > 0,40$
Slipperiness Resistance: Pendulum	UNE 41901:2017 EX DB SUA (actual)		Class 2	from Class 0 to Class 3
Slipperiness Resistance: Pendulum	BS7976-2:2002 / BSEN13036-4:2011		>36	0 - 24 Slippery; 25 - 35 Moderately slippery; 36+ Low slipping risk
Dynamic coefficient of friction (DCOF)	ANSI A326.3:2017		>0,42	$\geq 0,42$

* The work size shall be chose, for non-modular tiles, so that the difference between the work size and the nominal size is:

** The deviation, in percent, of the average size for each tile (2 or 4 sides) from the work size..

**** See Table 2 for uses where it is applicable

c.c. Centre curvature, related to diagonal calculated from the work sizes

e.c. Edge curvature, related to the corresponding work sizes.

w. Warpage, related to diagonal calculated from the work sizes.



Marazzi Group Srl a Socio Unico Viale Regina Pacis, 39 41049 Sassuolo (MO) Italy
T +39 0536 860800 F +39 0536 860644 info@marazzi.it www.marazzi.it

Cap.Soc. Euro102.232.000 Int.Vers. P.Iva e Cod. Intrastat IT 00611410374 C.F. EN di Iscrizione Reg. Impr. de Mo 00611410374 R.E.A. Modena N. 49219 N. Meccanografico MO 041028 Società soggetta a discrezione e coordinamento di Mohawk Industries, Inc.

TECHNICAL FEATURES

Collection: Cementum Surface: Natural	Brand: Marazzi
Size (cm): 120x120 RT	Thickness (mm): 06

[PAGINA VOLUTAMENTE LASCIATA IN BIANCO]
 [PAGE INTENTIONALLY LEFT BLANK]
 [PAGINA DEJADA EN BLANCO INTENCIONADAMENTE]
 [CETTE PAGE A ETE LAISSEE DELIBEREMENT BLANCHE]
 [SEITE WURDE ABSICHTLICH LEER GELASSEN]

