

| TECHNICAL FEATURES | |
|--|---------------------|
| Collection: Treverkstage Surface: Naturale | Brand: Marazzi |
| Size (cm): 20X120 | Thickness (mm): 9,5 |

Compliant with standard EN 14411:2016 annex G group Bla - GL
 Compliant with standard ISO 13006:2016 annex G group Bla - GL

| Technical Features | Testing Method | Meas. unit | Average Typical Values | Established limits |
|---|-----------------|----------------------|-----------------------------|---|
| DIMENSIONAL PROPERTIES AND SURFACE QUALITY | | | | |
| Dimensions | | | | Nominal Length of edge N (cm) 7≤N<15 Nominal Length of edge N (cm) N≥15 |
| Length and width (*) | ISO 10545-2 | (mm) (%) | Complies with the standards | ±2% (max 5mm) ±2% (max 5mm) ±2% (max 5mm) |
| Length and width (**) | | | Complies with the standards | ±0,9 mm ±0,6% ±2,0 mm |
| Thickness | | | Complies with the standards | ±0,5 mm ±5% ±0,5 mm |
| Straightness of sides | | | Complies with the standards | ±0,75 mm ±0,5% ±1,5 mm |
| Rectangularity | | | Complies with the standards | ±0,75 mm ±0,5% ±2,0 mm |
| Surface Flatness c.c - e.c. - w. | | | Complies with the standards | ±0,75 mm ±0,5% ±2,0 mm |
| Surface Quality | | (%) | Complies with the standards | ≥95% |
| PHISICAL PROPERTIES | | | | |
| Water absorption | ISO 10545-3 | (%) | ≤ 0,5 | Eb ≤ 0,5 (Individual maximum value 0,6%) |
| Modulus of rupture | ISO 10545-4 | (N/mm ²) | ≥ 35 | R ≥35 (Individual minimum value 32 N/mm ²) |
| Breaking Strength | ISO 10545-4 | (N) | ≥ 1300 | ≥1300 (Thickness ≥7,5 mm) ≥700 (Thickness < 7,5 mm) |
| Resistance to surface abrasion | Internal Method | | Intended use - Class G | |
| Linear thermal expansion coefficient | ISO 10545-8 | (x(10)-6/°C) | ≤9 | Declared value (EN 14411:2016) Test Method available (ISO 13006:2016) |
| Thermal shock resistance | ISO 10545-9 | | Complies with the standards | Declared value (EN 14411:2016) **** Test Method available (ISO 13006:2016) |
| Crazing Resistance | ISO 10545-11 | | Complies with the standards | Pass according to EN ISO 10545-1 (EN 14411:2016) Required (ISO 13006:2016) |
| Frost resistance | ISO 10545-12 | | Complies with the standards | Pass according to EN ISO 10545-1 (EN 14411:2016) Required (ISO 13006:2016) |
| Reaction to fire | - | - | Floor/Wall Class A1 FL / A1 | Class A1 or Class A1 FL (EN 14411:2016) |
| Colour resistance to light exposure | DIN 51094 | | Complies with the standards | No sample must show noticeable colour modifications. |

| TECHNICAL FEATURES | |
|--|---------------------|
| Collection: Treverkstage Surface: Naturale | Brand: Marazzi |
| Size (cm): 20X120 | Thickness (mm): 9,5 |

| Technical Features | Testing Method | Meas. unit | Average Typical Values | Established limits |
|---|----------------|------------|------------------------|--|
| CHEMICAL PROPERTIES | | | | |
| Resistance to chemicals for household use and swimming pool salts | ISO 10545-13 | | A | GB Minimum (EN 14411:2016) GB Minimum (ISO 13006:2016) |
| Resistance to low concentrations of acids and alkalis | ISO 10545-13 | | LA-LB | Declared value (EN 14411:2016) Test Method available (ISO 13006:2016) |
| Resistance to high concentrations of acids and alkalis | ISO 10545-13 | | HA-HB | Declared value (EN 14411:2016) Test Method available (ISO 13006:2016) |
| Stain resistance | ISO 10545-14 | | Class 5 | Minimum class 3 (EN 14411:2016) Minimum class 3 (ISO 13006:2016) |

| ANTISLIPPERY PROPERTIES | | | | |
|--|--------------------------------|--|--------------|-------------------------|
| Slipperiness Resistance: Ramp Method | DIN 51130 B.G.R. 181 | | R10 | from R9 to R13 |
| Slipperiness Resistance: B.C.R. | D.M. N.236 14/6/89 | | $\mu > 0,40$ | $\mu > 0,40$ |
| Slipperiness Resistance: Pendulum | ENV 12633 BOE N.74 del 2006 | | Class 1 | From Class 0 to Class 3 |
| Dynamic coefficient of friction (DCOF) | ANSI A137.1:2012 | | $>0,42$ | $\geq 0,42$ |

* The work size shall be chose, for non-modular tiles, so that the difference between the work size and the nominal size is:

** The deviation, in percent, of the average size for each tile (2 or 4 sides) from the work size..

**** See Table 2 for uses where it is applicable

c.c. Centre curvature, related to diagonal calculated from the work sizes

e.c. Edge curvature, related to the corresponding work sizes.

w. Warpage, related to diagonal calculated from the work sizes.

TECHNICAL FEATURES

| | |
|---|---------------------|
| Collection: Treverkstage Surface: Naturale | Brand: Marazzi |
| Size (cm): 20X120 | Thickness (mm): 9,5 |

[PAGINA VOLUTAMENTE LASCIATA IN BIANCO]
[PAGE INTENTIONALLY LEFT BLANK]
[PAGINA DEJADA EN BLANCO INTENCIONADAMENTE]
[CETTE PAGE A ETE LAISSEE DELIBEREMENT BLANCHE]
[SEITE WURDE ABSICHTLICH LEER GELASSEN]