

TECHNICAL FEATURES			
Collection: Mystone silver root r10		Brand: Marazzi	
Size (cm): 120x120 RT - 60x120 RT - 60x60 RT - 90x180 RT		Thickness (mm): 09	

Compliant with standard EN 14411:2016 annex G group Bla - UGL
Compliant with standard ISO 13006:2018 annex G group Bla - UGL

Technical Features	Testing Method	Meas. unit	Average Typical Values	Established limits			
DIMENSIONAL PROPERTIES AND SURFACE QUALITY							
Dimensions	ISO 10545-2 (mm) (%)			Nominal Length of edge N (cm) 7≤N<15		Nominal Length of edge N (cm) N≥15	
Length and width (*)				±2% (max 5mm)		±2% (max 5mm)	±2% (max 5mm)
Length and width (**)							
Not Rectified				Complies with the standards	±0,9 mm	±0,6%	±2,0 mm
Rectified					± 0,4 mm	±0,3 %	±1,0 mm
Thickness							
Not Rectified				Complies with the standards	±0,5 mm	±5%	±0,5 mm
Rectified					±0,5 mm	±5%	±0,5 mm
Straightness of sides							
Not Rectified				Complies with the standards	±0,75 mm	±0,5 %	±1,5 mm
Rectified					±0,4 mm	±0,3 %	±0,8 mm
Rectangularity							
Not Rectified				Complies with the standards	±0,75 mm	±0,5%	±2,0 mm
Rectified					±0,4 mm	±0,3%	±1,5 mm
Surface Flatness c.c - e.c. - w.							
Not Rectified				Complies with the standards	±0,75 mm	±0,5%	±2,0 mm
Rectified					±0,6 mm	±0,4%	±1,8 mm
Surface Quality					Complies with the standards		≥95%
PHYSICAL PROPERTIES							
Water absorption	ISO 10545-3	(%)	≤ 0,5	Eb ≤ 0,5 (Individual maximum value 0,6%)			
Color Uniformity (8)	ASTM C609 and Section 9.3		Compliant	V0 – 3 Judds			
Modulus of rupture	ISO 10545-4	(N/mm2)	≥ 35	R ≥35 (Individual minimum value 32 N/mm2)			
Breaking Strength	ISO 10545-4	(N)	≥ 1300	≥1300 (Thickness ≥7,5 mm) ≥700 (Thickness < 7,5 mm)			
Resistance to deep abrasion	ISO 10545-6	(mm3)	≤ 175	≤175			
Linear thermal expansion coefficient	ISO 10545-8	(x(10)-6/°C)	≤ 9	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)			
Deep Abrasion Resistance	ASTM C1243		Compliant	Max value (loss in mm3): 175 mm3 (0.011 in3)			
Thermal shock resistance	ISO 10545-9		Complies with the standards	Declared value (EN 14411:2016) **** Test Method available (ISO 13006:2018)			
Thermal Shock (5)	ASTM C484		Pass	Pass			
Frost resistance	ISO 10545-12		Complies with the standards	Pass according to EN ISO 10545-1 (EN 14411:2016) Required (ISO 13006:2018)			
Resistance to Freeze/ Taw Cycling	ASTM C1026		No damage	Declared Value			
Reaction to fire	-	-	A1 FL / A1	Class A1 or Class A1 FL			
Color resistance to light exposure	DIN 51094		Complies with the standards	No sample must show noticeable colour modifications.			
Bond Strength	ASTM C482		Compliant	≥ 50 psi (0.34 MPa)			



TECHNICAL FEATURES	
Collection: Mystone silver root r10	Brand: Marazzi
Size (cm): 120x120 RT - 60x120 RT - 60x60 RT - 90x180 RT	Thickness (mm): 09



TECHNICAL FEATURES	
Collection: Mystone silver root r10	Brand: Marazzi
Size (cm): 120x120 RT - 60x120 RT - 60x60 RT - 90x180 RT	Thickness (mm): 09

Technical Features	Testing Method	Meas. unit	Average Typical Values	Established limits
CHEMICAL PROPERTIES				
Resistance to chemicals for household use and swimming pool salts	ISO 10545-13		A	UB Minimum (EN 14411:2016) UB Minimum (ISO 13006:2018)
Resistance to low concentrations of acids and alkalis	ISO 10545-13		LA-LB	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)
Resistance to high concentrations of acids and alkalis	ISO 10545-13		HA-HB	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)
Stain resistance	ISO 10545-14		Class 5	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)

ANTISLIPPERY PROPERTIES				
Slipperiness Resistance: Ramp Method	DIN EN 16165 Annex B (ex DIN 51130); ASR A1.5		R10	from R9 to R13
Slipperiness Resistance: Ramp Method	DIN EN 16165 Annex A (ex DIN 51097) DGUV Information 207-006		B(A+B)	from A to C
Slipperiness Resistance: B.C.R.	D.M. N.236 14/6/89		μ > 0,40	μ > 0,40
Slipperiness Resistance: Pendulum	UNE EN 16165 Appendix C (ex UNE 41901:2017 EX - DB SUA)		Class 2	from Class 0 to Class 3
Slipperiness Resistance: Pendulum	BS7976-2:2002 / BSEN13036-4:2011		>36 (Slider 96)	0 - 24 Slippery; 25 - 35 Moderately slippery; 36+ Low slipping risk
Dynamic coefficient of friction (DCOF)	ANSI 326:3:2021		≥ 0,42 wet - IW	Interior Dry (ID) ≥ 0,42 dry, Interior Wet (IW) ≥ 0,42 wet, Interior Wet+ (IW+): Declared Value, Exterior Wet (EW): Declared Value
Slipperiness Resistance: Wet Pendulum Test Method	AS 4586-2013 Annex A		P3	from P0 to P5

* The work size shall be chose, for non-modular tiles, so that the difference between the work size and the nominal size is:
** The deviation, in percent, of the average size for each tile (2 or 4 sides) from the work size..
**** See Table 2 for uses where it is applicable
c.c. Centre curvature, related to diagonal calculated from the work sizes
e.c. Edge curvature, related to the corresponding work sizes.
w. Warpage, related to diagonal calculated from the work sizes.



TECHNICAL FEATURES	
Collection: Mystone silver root r10	Brand: Marazzi
Size (cm): 120x120 RT - 60x120 RT - 60x60 RT - 90x180 RT	Thickness (mm): 09

[PAGINA VOLUTAMENTE LASCIATA IN BIANCO]
[PAGE INTENTIONALLY LEFT BLANK]
[PAGINA DEJADA EN BLANCO INTENCIONADAMENTE]
[CETTE PAGE A ETE LAISSEE DELIBEREMENT BLANCHE]
[SEITE WURDE ABSICHTLICH LEER GELASSEN]

