

Formatos:(mm) 198x248x7,0 * 198x298x7,0 * 200x400x7,0 * 250x400x7,0 * 198x498x7,8 * 248x498x7,8

CARACT. DIMENSIONAIS * CARACTÉRISTIQUES MENSURABLES * DIMENSIONAL DATA	Características Técnicas Caractéristiques Techniques Technical Data		Norma de Ensaio Norme D'Essai Testing Standard	Requisito Norma Norme Condition Norm Requirement	Resultado Ceragni Résultats Ceragni Ceragni Results	Avaliação Évaluation Valuation
		DIMENSÕES	NP EN ISO 10545-2	Desvio admissível (%) da dimensão média de cada azulejo relativamente à média de fabricação (W): +/- 0,5%	+/- 0,5%	Conforme
		DIMENSIONS		Écart moyen d'un carreau / côte de fabrication (W): +/- 0,5 %		Conforme
		SIZES		The deviation in % of the average size for each tile from (W): +/- 0,5 %		Conforms
		TOLERÂNCIA DE ESPESSURA	NP EN ISO 10545-2	+/- 0,5 mm	0,2 mm	Conforme
		TOLÉRANCE DE L'ÉPAISSEUR				Conforme
		THICKNESS TOLERANCE				Conforms
		RECTILINEARIDADE DAS ARESTAS	NP EN ISO 10545-2	+/- 0,3 %	+/- 0,2 %	Conforme
		RECTILIGNILÉ DES CÔTES				Conforme
		STRAIGHTNESS OF EDGES				Conforms
	ORTOGONALIDADE	NP EN ISO 10545-2	+/- 0,5 %	+/- 0,3 %	Conforme	
	ORTHOGONALITÉ				Conforme	
	SQUARENESS				Conforms	
	PLANARIDADE	NP EN ISO 10545-2	Curvatura central +0,5% / -0,3% * lateral +0,5% / -0,3% * Empeno diagonal +/- 0,5%	-0,3 / 0,5 %	Conforme	
	PLANÉITÉ		Déformation centrale +0,5% / -0,3% * latérale +0,5% / -0,3% * distorsion diagonale +/- 0,5%		Conforme	
	FLATNESS		Central curvature +0,5% / -0,3% * lateral +0,5% / -0,3% * Warpage curvature +/- 0,5%		Conforms	
CARACTERÍSTICAS FÍSICAS * CARACTÉRISTIQUES PHYSIQUES * PHYSICAL DATA		ABSORÇÃO DE ÁGUA	NP EN ISO 10545-3	>10%	14 ... 19%	Conforme
		ABSORPTION D'EAU				Conforme
		WATER ABSORPTION				Conforms
		MÓDULO DE RUPTURA	NP EN ISO 10545-4	(<7,5mm) ≥ 12N/mm2 (≥7,5mm) ≥15N/mm2	(<7,5mm) ≥ 16N/mm2 (≥7,5mm) ≥16N/mm2	Conforme
		FORCE DE RUPTURE				Conforme
		MODULUS OF RUPTURE				Conforms
		RESISTÊNCIA À FLEXÃO	NP EN ISO 10545-4	(<7,5mm) ≥200N (≥7,5mm) ≥600N	(<7,5mm) > 300 N (≥7,5mm) > 600 N	Conforme
RÉSISTANCE À LA FLEXION		Conforme				
BREAKING STRENGTH		Conforms				
	RESIST.À FENDILHAGEM	NP EN ISO 10545-11	Exigida Exigée Required	Resistente Résistant Resistant	Conforme	
	RÉSIST. AU TRESSAILLAGE				Conforme	
	CRASING RESISTANCE				Conforms	
CARACTERÍSTICAS QUÍMICAS * CARACTÉRISTIQUES CHIMIQUES * CHEMICAL DATA		RESIST. A BAIXAS CONCENTRAÇÕES DE ÁCIDOS / BASES	NP EN ISSO 10545-13	min. LB	Garantido	Conforme
		RÉSIST. AUX BAISSSES CONCENTRATIONS DES PRODUITS ACIDS ET BASICS			Garanti	Conforme
		RESIST. TO LOW CONCENTRATION OF ACIDS AND ALKALIS			Guaranted	Conforms
		RESIST. AOS PRODUTOS QUÍMICOS DE LIMPEZA	NP EN ISSO 10545-13	min. LB	Garantido	Conforme
		RÉSIST. AUX PRODUITS CHIMIQUES D'EMPLOI DOMESTIQUES			Garanti	Conforme
		RESIST. HOUSEHOLD CHEMICALS			Guaranted	Conforms
		RESIST.ÀS MANCHAS	NP EN ISO 10545-14	min. Classe 3	Classe 5	Conforme
		RÉSIST. AUX PRODUITS TÂCHANTS				Conforme
STAIN RESISTANCE		Conforms				
EMBALAGEM - COLISAGE - PACKAGING						
Formato (cm) Size (cm) Taille (cm)		Peças / Caixa Pieces / Box Pièces / Boîte	M2/Caixa M2 / BOX M2/Carton	M2 / Palette M2 / Pallet M2 / Palette	Kg /Palette Kgs / Pallet Kgs / Palette	
M20x25		20	1	96	1130	
M20x30		17	1	92	1090	
M20x30		25	1,5	96	1090	
20x40		15	1,2	86,4	1100	
25x40		10	1	72	920	
25x40		15	1,5	81	1010	
M20x50		12	1,2	86,4	1120	
M25x50		12	1,5	81	1052	