

TECHNICAL FEATURES	
Collection: Grande stone look Surface: Natural	Brand: Marazzi
Size (cm): 120x120 RT - 120x240 RT - 120x278 RT - 160x320 RT	Thickness (mm): 06
Colour: Ceppo di gre - pietra di vals	

Compliant with standard EN 14411:2016 annex G group Bla - GL

Compliant with standard ISO 13006:2018 annex G group Bla - GL

Technical Features	Testing Method	Meas. unit	Average Typical Values	Established limits			
DIMENSIONAL PROPERTIES AND SURFACE QUALITY							
Dimensions				Nominal Length of edge N (cm) 7≤N<15	Nominal Length of edge N (cm) N≥15		
Length and width (*)	ISO 10545-2	(mm) (%)	Complies with the standards	±2% (max 5mm)	±2% (max 5mm) ±2% (max 5mm)		
Length and width (**)							
Not Rectified			Complies with the standards	±0,9 mm	±0,6%	±2,0 mm	
Rectified				± 0,4 mm	±0,3 %	±1,0 mm	
Thickness							
Not Rectified			Complies with the standards	±0,5 mm	±5%	±0,5 mm	
Rectified				±0,5 mm	±5%	±0,5 mm	
Straightness of sides							
Not Rectified			Complies with the standards	±0,75 mm	±0,5 %	±1,5 mm	
Rectified				±0,4 mm	±0,3 %	±0,8 mm	
Rectangularity							
Not Rectified			Complies with the standards	±0,75 mm	±0,5%	±2,0 mm	
Rectified				±0,4 mm	±0,3%	±1,5 mm	
Surface Flatness c.c - e.c. - w.							
Not Rectified			Complies with the standards	±0,75 mm	±0,5%	±2,0 mm	
Rectified				±0,6 mm	±0,4%	±1,8 mm	
Surface Quality				Complies with the standards	≥95%		
PHYSICAL PROPERTIES							
Water absorption	ISO 10545-3	(%)	<= 0,1	Eb ≤ 0,5 (Individual maximum value 0,6%)			
Modulus of rupture	ISO 10545-4	(N/mm2)	>= 35	R ≥35 (Individual minimum value 32 N/mm2)			
Breaking Strength	ISO 10545-4	(N)	>= 700	≥1300 (Thickness ≥7,5 mm) ≥700 (Thickness < 7,5 mm)			
Resistance to surface abrasion	Internal Method		Intended use - Class H				
Linear thermal expansion coefficient	ISO 10545-8	(x(10)-6/°C)	<=9	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)			
Thermal shock resistance	ISO 10545-9		Complies with the standards	Declared value (EN 14411:2016) **** Test Method available (ISO 13006:2018)			
Crazing Resistance	ISO 10545-11		Complies with the standards	Pass according to EN ISO 10545-1 (EN 14411:2016) Required (ISO 13006:2018)			
Frost resistance	ISO 10545-12		Complies with the standards	Pass according to EN ISO 10545-1 (EN 14411:2016) Required (ISO 13006:2018)			
Reaction to fire	-	-	A1 FL / A1	Class A1 or Class A1 FL (EN 14411:2016)			
Color resistance to light exposure	DIN 51094		Complies with the standards	No sample must show noticeable colour modifications.			



Marazzi Group Srl a Socio Unico Viale Regina Pacis, 39 41049 Sassuolo (MO) Italy
T +39 0536 860800 F +39 0536 860644 info@marazzi.it www.marazzi.it

Cap.Soc. Euro102.232.000 Int.Vers. Pl.Iva e Cod. Intrastat IT 00611410374 C.F. EN di Iscrizione Reg. Impr. de Mo 00611410374 R.E.A. Modena N. 49219 N. Meccanografico MO 041028 Società soggetta a discrezione e coordinamento di Mohawk Industries, Inc.

TECHNICAL FEATURES	
Collection: Grande stone look Surface: Natural	Brand: Marazzi
Size (cm): 120x120 RT - 120x240 RT - 120x278 RT - 160x320 RT	Thickness (mm): 06
Colour: Ceppo di gre - pietra di vals	

Technical Features	Testing Method	Meas. unit	Average Typical Values	Established limits
CHEMICAL PROPERTIES				
Resistance to chemicals for household use and swimming pool salts	ISO 10545-13		A	GB Minimum (EN 14411:2016) GB Minimum (ISO 13006:2018)
Resistance to low concentrations of acids and alkalis	ISO 10545-13		LA-LB	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)
Resistance to high concentrations of acids and alkalis	ISO 10545-13		HA-HB	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)
Stain resistance	ISO 10545-14		Class 5	Minimum class 3 (EN 14411:2016) Minimum class 3 (ISO 13006:2018)

ANTISLIPPERY PROPERTIES				
Slipperiness Resistance: Ramp Method	DIN EN 16165 Annex B (ex DIN 51130); ASR A1.5		R10	from R9 to R13
Slipperiness Resistance: B.C.R.	D.M. N.236 14/6/89		$\mu > 0,40$	$\mu > 0,40$
Slipperiness Resistance: Pendulum	UNE EN 16165 Appendix C (ex UNE 41901:2017 EX - DB SUA)		Class 1	From Class 0 to Class 3
Dynamic coefficient of friction (DCOF)	ANSI 326:3:2021		$> 0,42$	Interior Dry (ID) $\geq 0,42$ dry, Interior Wet (IW) $\geq 0,42$ wet, Interior Wet+ (IW+): Declared Value, Exterior Wet (EW): Declared value

* The work size shall be chose, for non-modular tiles, so that the difference between the work size and the nominal size is:

** The deviation, in percent, of the average size for each tile (2 or 4 sides) from the work size..

**** See Table 2 for uses where it is applicable

c.c. Centre curvature, related to diagonal calculated from the work sizes

e.c. Edge curvature, related to the corresponding work sizes.

w. Warpage, related to diagonal calculated from the work sizes.



Marazzi Group Srl a Socio Unico Viale Regina Pacis, 39 41049 Sassuolo (MO) Italy
T +39 0536 860800 F +39 0536 860644 info@marazzi.it www.marazzi.it

Cap.Soc. Euro102.232.000 Int.Vers. P.Iva e Cod. Intrastat IT 00611410374 C.F.E.N di Iscrizione Reg. Impr. de Mo 00611410374 R.E.A. Modena N. 49219 N. Meccanografico MO 041028 Società soggetta a discrezione e coordinamento di Mohawk Industries, Inc.

TECHNICAL FEATURES	
Collection: Grande stone look Surface: Natural	Brand: Marazzi
Size (cm): 120x120 RT - 120x240 RT - 120x278 RT - 160x320 RT	Thickness (mm): 06
Colour: Ceppo di gre - pietra di vals	

[PAGINA VOLUTAMENTE LASCIATA IN BIANCO]
[PAGE INTENTIONALLY LEFT BLANK]
[PAGINA DEJADA EN BLANCO INTENCIONADAMENTE]
[CETTE PAGE A ETE LAISSEE DELIBEREMENT BLANCHE]
[SEITE WURDE ABSICHTLICH LEER GELASSEN]

