

ISOCORE 2.0

TECHNICAL DATA SHEET

CELLO

PHYSICAL PROPERTIES & PACKAGING (ISOCORE FLOORING - 6.3 / 0.55 MM)		
Collection	PLANK	
Use	Commercial & Residential	
Size	220x 1210 mm	
Thickness - Overall	6.3 mm	
Product Construction	4.0 mm ISOCORE Technology® 1.5 mm Luxury Vinyl Tile (LVT) 0.8 mm IXPE	
Wear Layer - Thickness	0.55mm	
Edge Detail	4 sides bevelled	
Embossing	IRE embossing	
Patented Click System	DL100	
Mass per Unit Area	6.325 kg/m2	
Pieces/Carton	7 Pieces	
Coverage/Carton	1.86 m²	
Coverage/Pallet	44 Cartons (81.84 m²)	
Coverage/Container	30 Pallets (2455.20 m²)	
Warranty ⁽¹⁾	Material: 20 years (100%) Labour: 10 years (Pro rata)	

EUROPEAN / INTERNATIONAL STANDARDS - CE CERTIFICATION / TESTING			
Description	Standard	Symbol	Results
CE Certification	EN 14041		Refer to Standards Below
Reaction to Fire (and Smoke Production)	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2		Bfl - s1
Formaldehyde Emission	EN 717-1		Class E1
Content of PCP (Pentachlorophenol)	EN 12673:1999		Not detected
Slip Resistance (Dry)	EN 13893		Class DS
Static Electrical Propensity	EN 1815, Method A		Antistatic ≤2,0kV (Absolute Value)
Thermal Resistance Thermal Conductivity	EN 12664		R23 = 0.077(m2 . K)/W λ23 = 0.081W/m . K

ISOCORE 2.0

TECHNICAL DATA SHEET

CELLO

EUROPEAN / INTERNATIONAL STANDARDS - MANUFACTURING & USAGE (EN 16511)			
Description	Standard	Symbol	Results
Classification (Level of Use)	EN 16511 EN ISO 10874		Commercial - Heavy (Class 33) Refers to standard below
Wear Resistance IP	ISO 24338 Procedure A ,		≥ 5000 cycles
Impact Resistance (Big Ball)	EN 13329:2006+A1:2008, Annex F		No Damage
Micro-Scratch Resistance [Class]	EN 16094, Method A	N/A	MSR-A2
Castor Chair Resistance	EN ISO 4918		After 25,000 cycles: No Disturbance to the Surface; No Delamination, Cracks, or Disruptions
Effect of Furniture Leg	EN ISO 16581 (tested with foot type 0)		No Visible Damage
Residual Indentation	EN ISO 24343-1		≤0.15mm
Resistance to Staining [Grade, per Group]	EN 438-2 (Group 1 & 3 - Only 10 Minutes)		Groups 1, 2 & 3: Grade 5
Locking Strength	ISO 24334		Long Side ≥ 1.0 kN/m Short Side ≥ 1.5 kN/m
Dimensional stability under influence of temperature and Curling	EN ISO 23999		≤0.15% ≤< 2 mm
Thickness (t)	EN 17539		$\Delta t_{avg} \leq 0.50\text{mm}$ (Versus Nominal) $t_{max} - t_{min} \leq 0.50\text{mm}$
Length (l)	EN 17539		$l \leq 1500\text{mm}$: $\Delta l \leq 0.5\text{mm}$ $l > 1500\text{mm}$: $\Delta l \leq 0.3\text{mm/m}$ (Versus Nominal)
Width (w)			$\Delta_{wavg} \leq 0.10\text{mm}$ (Versus Nominal) $w_{max} - w_{min} \leq 0.20\text{mm}$
Squareness (q)			$q_{max} \leq 0.20\text{mm}$
Straightness (s)			$s_{max} \leq 0.30\text{mm/m}$
Flatness (f)	EN 17539	N/A	Maximum Single Values: $f_{w,concave} \leq 0.15\%$, $f_{w,convex} \leq 0.20\%$ $f_{l,concave} \leq 0.50\%$, $f_{l,convex} \leq 1.00\%$
Openings (o)	EN 17539	N/A	Measured from the Surface Between Vertical, Contacting Edges: $o_{avg} \leq 0.15\text{mm}$, $o_{max} \leq 0.20\text{mm}$
Height Difference (h)	EN 17539	N/A	$h_{avg} \leq 0.10\text{mm}$ $h_{max} \leq 0.15\text{mm}$

ISOCORE 2.0

TECHNICAL DATA SHEET

CELLO

EUROPEAN / INTERNATIONAL STANDARDS - AUXILIARY PERFORMANCE & SAFETY			
Description	Standard	Symbol	Results
Colour Fastness to Light	ISO 105-B02, Method 3		≥Grade 6
Slip Resistance (Wet)	DIN EN 16165 Annex B, C	N/A	R10 Low Slip Potential
Resistance to Staining	EN ISO 26987:2012		INDEX 0
Impact Sound Insulation ⁽²⁾	EN ISO 10140-3 ISO 717-2 EN ISO 140-8		$\Delta L_w = 19$ dB
A-weighted walking sound pressure level	EN 16205:2013		$L_{n,walk'} A = 80$ dB(A)
Product-Content Safety	REACH SVHC	N/A	Not Detected

Footnotes

- 1) **Warranty:** Please see full terms and conditions of our warranties at www.aspectaflooring.com
- 2) **Impact Sound Insulation (EN ISO 10140-3, ISO 717-2, EN ISO 140-8):** ΔLW = Weighted Reduction of Impact Sound Pressure Level

The manufacturing facility is ISO 9001 (Quality Management System) and ISO 14001(Environmental Management System) certified.

Disclaimer: This document represents the current state of knowledge at the time of its publication and instantly supersedes all previous editions. It may be replaced, supplemented or amended at any time and without special notice. Please be sure to check the validity, relevance and content for topicality before issuing a guarantee claim at www.aspectaflooring.com

