

Name of The Product : 9,7x9,7 Uma Series (30x40)  
Production Facility : Floor Tile Factory  
Product Group : Dry-pressed ceramic tiles / Group BIb/ GL  
Recommended Use : Interior & exterior floor  
General Properties : Mat  
Report Date : 10.07.2025

Test Title	Test Results	Requirements	Decision
Length & Width (mm)	96,8 x 97,3 mm	96,5 – 97,5 mm	OK
Thickness (mm)	7,0 mm	6,7 – 7,3 mm	OK
Straightness of Sides (%)	± %0,2	± %0,5	OK
Rectangularity (%)	± %0,2	± %0,6	OK
Edge Curvature (%)	± %0,2	± %0,5	OK
Corner Curvature (%)	± %0,2	± %0,5	OK
Center Curvature (%)	± %0,2	± %0,5	OK
Small Colour Differences	First Quality	> %95 perfect	OK
Water Absorption	2,0 %	0,5 % < E ≤ 3,0 %	OK
Breaking Strength (N)	> 1100 N	> 700 N	OK
Modulus of Rupture (N/m m <sup>2</sup> )	> 33 N/mm <sup>2</sup>	> 30 N/mm <sup>2</sup>	OK
Abrasion Resistance (PEI)	White:IV Antrasit:III Beige:III Grey:III	As declared	OK
Coeff. Of Thermal Expansion	< 7,0 x 10 <sup>-6</sup>	As declared	OK
Thermal Shock Resistance	Resistant	Required	OK
Crazing Resistance	Resistant	Required	OK
Frost Resistance	Resistant	Required	OK
Coefficient of Friction (μ)	~0,62	As declared	OK
Moisture Expansion (mm/m)	< 0,3	As declared	OK
Impact Resistance	Resistant	As declared	OK
Staining Resistance	Class 5	Min. Class 3	OK
Resistance to low conc. of Acid & Alkalis	B	As declared	OK
Resistance to high conc. of Acid & Alkalis	B	As declared	OK
Household Chemicals	A	Min. B	OK
Release of Cad mium	< 0,07 mg/dm <sup>2</sup>	As declared	OK
Release of Lead	< 0,8 mg/dm <sup>2</sup>	As declared	OK
OVERALL RESULT	All test results are positive according to the norms of ISO 13006 and EN 14411 standards, Annex H.		

**Prepared by**  
Kağan Kurnaz  
Quality Assurance Staff



**Approved by**  
Ahmet Pehlivan  
Quality Assurance Manager

