


TECHNICAL FEATURES

MODEL:	CONSTANZA MOCHA
FORMAT:	60x60n(C)
THICKNESS(mm):	9
DATE:	13/11/2025
CODE:	017.077.0210.15089
GROUP:	GRUPO BIa UNE-EN 14411 Anexo G / SASO GSO ISO 13006:2022 Anexo G
TILE TYPE:	GL
FINISH:	RECTIFIED MATT
FAMILY:	PORCELAIN TILES
NUMBER OF DESIGNS:	24



TEST	RESULT
UNE-EN ISO 10545-2	DIMENSIONAL FEATURES COMPLIES WITH THE STANDARD
UNE-EN ISO 10545-3	WATER ABSORPTION <= 0,5 %
UNE-EN ISO 10545-4	MODULUS OF RUPTURE - BREAKING STRENGTH 1600-2400 N
	MODULUS OF RUPTURE - BENDING STRENGTH 35-45 N/mm2
UNE-EN ISO 10545-6	RESISTANCE TO DEEP ABRASION (MM3) <130 mm3
UNE-EN ISO 10545-7	RESISTANCE TO SURFACE ABRASION -
UNE-EN ISO 10545-8	LINEAR THERMAL EXPANSION <7,0 x 10-6 °C-1
UNE-EN ISO 10545-9	THERMAL SHOCK RESISTANCE RESISTS
UNE-EN ISO 10545-11	CRAZING RESISTANCE RESISTS
UNE-EN ISO 10545-12	FROST RESISTANCE RESISTS
UNE-EN ISO 10545-13	CHEMICAL RESISTANCE - AMMONIUM CHLORIDE 100 G/L A
	CHEMICAL RESISTANCE - SODIUM HYPOCHLORITE 20 MG/L A
	CHEMICAL RESISTANCE - HYDROCHLORIC ACID 3% COMPLIES WITH THE STANDARD
	CHEMICAL RESISTANCE - CITRIC ACID 100 G/L COMPLIES WITH THE STANDARD
	CHEMICAL RESISTANCE - POTASSIUM HYDROXYDE 30 G/L COMPLIES WITH THE STANDARD
UNE-EN ISO 10545-14	STAIN RESISTANCE - GREEN AGENT IN LIGHT OIL 5
	STAIN RESISTANCE - IODINE SOLUTION IN ALCOHOL 5
	STAIN RESISTANCE - OLIVE OIL 5

SLIP RESISTANCE

TEST		RESULT
	EN 16165:2022 Anexo C	SLIP RESISTANCE (PENDULUM)
		CLASE 1
	EN 16165:2022 Anexo A - Pie calzado	CRITICAL ANGLE OF SLIP (INCLINED PLATFORM)
		R10
	EN 16165:2022 Anexo A - Pie descalzo	CRITICAL ANGLE OF SLIP. WET-LOADED BAREFOOT AREAS
		-
	BS7976 (PTV) WET	CLASSIFICATION ACCORDING TO PENDULUM TEST VALUES (PTV) WET
		36+
	EN 16165:2022 Anexo B	DYNAMIC COEFFICIENT OF FRICTION (DCOF) OF RIGID FLOORS.
		-

TEST	VALOR UPEC
<u>UPEC</u>	UPEC CERTIFICATION
	-

Declaration of Performance:

https://www.pamesa.com/ERP/4.0/empresas/151/045/ficheros/t00030006/113/DdP_DoP_N003CPR2013.pdf

TECHNICAL DEPARTMENT
PAMESA CERÁMICA